

Perspex® from Lucite® Technical Data Sheet

Table of Properties

Values quoted for the properties of Perspex® from Lucite® are the results of tests on representative samples and do not constitute specifications.

Property	Test Method	Units	GS CAST	GS IM CAST
General Properties				
Relative Density	ISO 1183	-	1.19	1.18
Rockwell Hardness	ISO 2039-2	M scale	102	98.5
Water Absorption	ISO 62	%	0.2	0.4
Flammability	BS 476 Pt 7	Class	3	3
	DIN 4102	-	B2	B2
	NFP 92-507	-	M4	-
	UL94	-	HB	HB
	ISO 11925-2	-	E	-
Mechanical Properties				
Tensile strength (5 mm/min)	ISO 527	MPa	75	62
Elongation at Break (5 mm/min)	ISO 527	%	4	-
Flexural Strength (2 mm/min)	ISO 178	MPa	116	105
Flexural Modulus (2 mm/min)	ISO 178	MPa	3210	2960
Impact Strength – Charpy (unnotched)	ISO 179	kJ.m ⁻²	12	21.7
	ISO 179	kJ.m ⁻²	-	1.2
Izod Impact Strength	ISO 180/1A	kJ.m ⁻²	-	-

>>



Talk to us
Tel: +44 (0)1254 874000
info@lucitesolutions.com
www.lucitesolutions.com

302/En//1009

LUCITE®
The source of inspiration

Technical Data Sheet

Values quoted for the properties of Perspex® from Lucite® are the results of tests on representative samples and do not constitute specifications.

Property	Test Method	Units	GS CAST	GS IM CAST
Thermal Properties				
Vicat Softening Point	ISO 306 A	°C	> 110	> 110
Coefficient of Thermal Expansion - Linear	ASTM D696	$\times 10^{-5} \cdot K^{-1}$	7.7	-
Optical Properties				
Light Transmission	ASTM D1003	% (0 mm)	> 92	> 92
Refractive Index	ISO 489 A		1.49	-
Electrical Properties				
Surface Resistivity	IEC 93	$\Omega \cdot m^{-2}$	$> 10^{14}$	-
Electrical Strength	IEC 243	$kV \cdot mm^{-1}$	15	-

The information is given in good faith and is based on our general experience, but because of the many particular factors which are outside our knowledge and control that affect the use of products, no warranty is given or is to be implied. Freedom from patent rights must not be assumed.