

## Perspex® from Lucite® Technical Data Sheet

### Table of Properties

Values quoted for the properties of Perspex® from Lucite® are the results of tests on representative samples and do not constitute specifications.

Property	Test Method	Units	0x00	IMPACT MODIFIED	
				IM50	IM60
<b>General Properties</b>					
Relative Density	ISO 1183	-	1.19	1.17	1.16
Rockwell Hardness	ISO 2039-2	M scale	101	65	45
Water Absorption	ISO 62	%	0.2	0.3	0.3
Flammability	DIN 4102	-	B2	B2	B2
	UL94	-	HB	HB	HB
	BS 476 Part 7	Class	4	-	-
	NFP 92-507		M4		
	ISO 11925-2	-	E	-	-
<b>Mechanical Properties</b>					
Tensile strength (5 mm/min)	ISO 527	MPa	70	68	50
Elongation at Break (5 mm/min)	ISO 527	%	4	18	25
Flexural Strength (2 mm/min)	ISO 178	MPa	107	90	70
Flexural Modulus (2 mm/min)	ISO 178	MPa	3030	2500	2000
Charpy Impact Strength (unnotched)	ISO 179	$\text{kJ.m}^{-2}$	10	50	65
	ISO 179	$\text{kJ.m}^{-2}$	-	5	7
Izod Impact Strength	ISO 180/1A	$\text{kJ.m}^{-2}$	-	5	7

>>



Talk to us  
Tel: +44 (0)1254 874000  
info@lucitesolutions.com  
www.lucitesolutions.com

302/En/1009

LUCITE®  
The source of inspiration

# Technical Data Sheet

Values quoted for the properties of Perspex® from Lucite® are the results of tests on representative samples and do not constitute specifications.

Property	Test Method	Units	0x00	IM50	IM60
<b>Thermal Properties</b>					
Vicat Softening Point	ISO 306 A	°C	> 105	> 105	> 105
Coefficient of Thermal Expansion	ASTM D696	$\times 10^{-5} \cdot K^{-1}$	7.8	-	-
<b>Optical Properties</b>					
Light Transmission	ASTM D1003	% (3 mm)	> 92	90	89
Refractive Index	ISO 489 A	-	1.49	-	-
<b>Electrical Properties</b>					
Surface Resistivity	IEC 93	$\Omega \cdot m^{-2}$	$> 10^{14}$	-	-
Electrical Strength	IEC 243	$kV \cdot mm^{-1}$	-	-	-

The information is given in good faith and is based on our general experience, but because of the many particular factors which are outside our knowledge and control that affect the use of products, no warranty is given or is to be implied. Freedom from patent rights must not be assumed.