

TORLON® 4203 & 4503 PAI

TORLON 4203 PAI offers the best toughness and impact strength of all TORLON PAI grades. Because of its intrinsic high temperature resistance, high dimensional stability and good machinability, this extruded TORLON PAI grade is very popular for precision parts in high-tech equipment. In addition, its good electrical insulating ability provides numerous possibilities in the field of electrical components. Compression moulded TORLON 4503 PAI is similar in composition to TORLON 4203 PAI, and is selected when larger shapes are required.

Physical properties (indicative values [■])

PROPERTIES	Test methods	Units	VALUES (15)
Colour	-	-	yellow-ochre
Density	ISO 1183-1	g/cm ³	1.41
Water absorption:			
- after 24/96 h immersion in water of 23°C (1)	ISO 62	mg	29 / -
	ISO 62	%	0.35 / -
- at saturation in air of 23°C / 50% RH	-	%	2.5
- at saturation in water of 23°C	-	%	4.4
Thermal Properties			
Melting temperature (DSC, 10°C/min)	ISO 11357-1/-3	°C	NA
Glass transition temperature (DSC, 20°C/min) - (2)	ISO 11357-1/-2	°C	280
Thermal conductivity at 23°C	-	W/(K.m)	0.26
Coefficient of linear thermal expansion:			
- average value between 23 and 100°C	-	m/(m.K)	30 x 10 ⁻⁶
- average value between 23 and 150°C	-	m/(m.K)	30 x 10 ⁻⁶
- average value above 150°C	-	m/(m.K)	30 x 10 ⁻⁶
Temperature of deflection under load:			
- method A: 1.8 MPa	ISO 75-1/-2	°C	280
Max. allowable service temperature in air:			
- for short periods (3)	-	°C	270
- continuously : for min. 20,000 h (4)	-	°C	250
Min. service temperature (5)	-	°C	-50
Flammability (6):			
- "Oxygen Index"	ISO 4589-1/-2	%	45
- according to UL 94 (1.5 / 3 mm thickness)	-	-	V-0 / V-0
Mechanical Properties at 23°C (7)			
Tension test (8):			
- tensile stress at yield / tensile stress at break (9)	ISO 527-1/-2	MPa	150 / -
- tensile strength (9)	ISO 527-1/-2	MPa	150
- tensile strain at break (9)	ISO 527-1/-2	%	20
- tensile modulus of elasticity (10)	ISO 527-1/-2	MPa	4200
Compression test (11):			
- compressive stress at 1 / 2 % nominal strain (10)	ISO 604	MPa	34 / 67
Charpy impact strength - unnotched (12)	ISO 179-1/1eU	kJ/m ²	no break
Charpy impact strength - notched	ISO 179-1/1eA	kJ/m ²	15
Ball indentation hardness (13)	ISO 2039-1	N/mm ²	200
Rockwell hardness (13)	ISO 2039-2	-	E 80 (M 120)
Electrical Properties at 23 °C			
Electric strength (14)	IEC 60243-1	kV/mm	24
Volume resistivity	IEC 60093	Ohm.cm	> 10 ¹⁴
Surface resistivity	ANSI/ESD STM 11.11	Ohm/sq.	> 10 ¹³
Relative permittivity ε _r : - at 100 Hz	IEC 60250	-	4.2
- at 1 MHz	IEC 60250	-	3.9
Dielectric dissipation factor tan δ: - at 100 Hz	IEC 60250	-	0.026
- at 1 MHz	IEC 60250	-	0.031
Comparative tracking index (CTI)	IEC 60112	-	-

Note: 1 g/cm³ = 1,000 kg/m³; 1 MPa = 1 N/mm²; 1 kV/mm = 1 MV/m.

NA: not applicable

Legend:

- (1) According to method 1 of ISO 62 and done on discs Ø 50 x 3 mm.
- (2) Values for this property are only given here for amorphous materials and not for semi-crystalline ones.
- (3) Only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
- (4) Temperature resistance over a period of min. 20,000 hours. After this period of time, there is a decrease in tensile strength – measured at 23°C – of about 50% as compared with the original value.
The temperature value given here is thus based on the thermal-oxidative degradation which takes place and causes a reduction in properties. Note, however, that the maximum allowable service temperature depends in many cases essentially on the duration and the magnitude of the mechanical stresses to which the material is subjected.
- (5) Impact strength decreasing with decreasing temperature, the minimum allowable service temperature is practically mainly determined by the extent to which the material is subjected to impact. The value given here is based on unfavourable impact conditions and may consequently not be considered as being the absolute practical limit.
- (6) These estimated ratings, derived from raw material supplier data and other publications, are not intended to reflect hazards presented by the materials under actual fire conditions. There is no 'UL File Number' available for TORLON 4203 PAI & TORLON 4503 PAI stock shapes.
- (7) Most of the figures given for the mechanical properties are average values of tests run on test specimens machined out of rod Ø 50 mm. Except for the hardness tests, the test specimens were then taken from an area mid between centre and outside diameter, with their length in longitudinal direction (parallel to the extrusion direction).
- (8) Test specimens: Type 1 B
- (9) Test speed: 50 mm/min [chosen acc. to ISO 10350-1 as a function of the ductile behaviour of the material (tough or brittle)]
- (10) Test speed: 1 mm/min.
- (11) Test specimens: cylinders Ø 8 x 16 mm
- (12) Pendulum used: 4 J.
- (13) Measured on 10 mm thick test specimens (discs), mid between centre and outside diameter.
- (14) Electrode configuration: Ø 25 / Ø 75 mm coaxial cylinders ; in transformer oil according to IEC 60296 ; 1 mm thick test specimens.
- (15) It has to be noted that the property values of compression moulded TORLON 4503 PAI stock shapes can significantly differ from those given in this table which apply to extruded TORLON 4203 PAI stock shapes. They have to be considered on an individual shape and dimension related basis. Please consult us.

This table is a valuable help in the choice of a material. The data listed here fall within the normal range of product properties of dry material. However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.

AVAILABILITY

TORLON 4203 PAI:

Round Rods: Ø 2.38-50.80 mm - **Plates:** Thicknesses 6.35-25.40 mm

TORLON 4503 PAI:

Round Rods: Ø 50.80-381.00 mm - **Tubes:** O.D. 44.45-882.65 mm

TORLON® is a registered trademark of Solvay Advanced Polymers

All information supplied by or on behalf of Quadrant Engineering Plastic Products in relation to its products, in any form, is supported by research and believed to be reliable, but Quadrant Engineering Plastic Products assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Quadrant Engineering Plastic Products for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.